



MAGNESIUM OXIDE OXIMAG™ HA

APPLICATION:

A vulcanizing agent in rubber production • a filler in production of rubber plastics, putties, adhesives • medicine and perfume • production of chemical agents • cleaning from oil products • production of various magnesium compounds • gas treatment • in food industry as emulsifier, anti-caking additive.

THE BASIC QUALITY PARAMETERS:

INDEX	DATA
Appearance	Light white powder with high porosity
1 Mass fraction of magnesium oxide, % , min	99*
2 Mass fraction of calcium oxide (CaO), %, max	0.2
3 Mass fraction of silicon dioxide (SiO ₂), %, max	0.05
4 Mass fraction of iron as Fe ₂ O ₃ , %, max	0.05
5 Mass fraction of aluminum oxide Al ₂ O ₃ , %, max	0.05
6 Mass fraction of chlorine (Cl ⁻), %, max	0.1
7 Mass fraction of sulfates SO ₄ %, max	0.1
8 Mass fraction of sodium + potassium (Na +K), %, max	0.1
9 Loss on ignition (900 °C), %, max	7.0
10 Specific surface area (BET), m ² /g,	100–170
11 Particle size: sieve residue with screen 325 mesh, %, max	1

*The norm is given based on the calcined product.

The material is produced as a tailor-made system. There is a strong producer/customer cooperation

CERTIFICATION:

ISO 9001; ISO 22000:2005; HACCP Codex Alimentarius; HALAL; KOSHER

CONTACT DETAILS:

Wijnhaven 3D, 3011 WG Rotterdam, The Netherlands, tel: +31102687013, e-mail: office@nikomag-europe.com